

Technical Data Sheet



Arteo Ceramin

Usage Class 34 acc. to DIN EN 16511:2023-07

Version: 05/2025

Profile:

easyloc
by CLASSEN

Core board:

Classen Ceramin-Board

Dimensions:

1290 x 203 x 4 mm

Quantity / Weight per box (PU):

10 pieces = 2.618 m² / approx. 17 kg

Quantity / Weight per pallet:

48 PU = 125.66 m² / approx. 807 kg

Surface structure:

Timberland MATT 56 T

Characteristics		Test Method	Requirements
General Requirements			
Geometrical characteristics		EN 17539	Length: ± 0.5 mm Width: ± 0.1 mm
Total thickness		EN 17539	± 0.5 mm
Flatness of the elements		EN 17539	Length: concave ≤ 0.50 %, convex ≤ 1.00 % Width: concave ≤ 0.15 %, convex ≤ 0.20 %
Squareness		EN 17539	max. ≤ 0.20 mm
Straightness		EN 17539	max. ≤ 0.30 mm/m
Openings		EN 17539	Ø ≤ 0.15 mm max. ≤ 0.20 mm
Height difference		EN 17539	Ø ≤ 0.10 mm max. ≤ 0.15 mm
Light fastness		EN ISO 105-B02	Grey scale level ≥ 4
Determination of dimensional stability and curling after exposure to heat		ISO 23999	Δl ≤ 0,15 % ≤ 2 mm
Classification Requirements			
Wear resistance		ISO 24338 (Method B)	≥ 7,000 Cycles
Impact resistance		EN 13329:2006	≥ 1,800 mm
Micro-scratch resistance		EN 16094	≤ MSR - A2 (l ≤ 1 unit change l at 60°)
Castor chair resistance		ISO 4918	No visible damage with type W (25,000 Cycles)
Movement of a furniture leg		ISO 16581	No visible damage with type 0
Residual indentation		EN ISO 24343-1	max. ≤ 0.15 mm
Resistance to staining		EN 438-2	5 (group 1 and 2), 4 (group 3)
Thickness swelling		ISO 24336	No swelling
Locking strength		ISO 24334	Long side ≥ 1.0 kN/m Short side ≥ 3.5 kN/m
Essential Characteristics			
Reaction to fire*		EN 13501-1	C _{fl} - s1
Slip resistance*		EN 13893	DS
Electrical behaviour		EN 1815	Not antistatic
Formaldehyde*		EN 16516	Not added
Thermal resistance*		EN 12667	R ≤ 0.015 (m ² K)/W
PCP-Content		CEN/TR 14823	PCP free
Additional Characteristics			
Composition		No halogenes or phthalates added	
VOC Emissions		www.blauer-engel.de/uz120 • emissionsarm • geringer Schadstoffgehalt • in der Wohnumwelt gesundheitlich unbedenklich	
Recycled content (Post Consumer)			

Disposal: Private: with normal household waste / bulky waste possible | Commercial: European Waste Catalog: Waste code 17 02 03

We guarantee consistency of our decor colours under artificial light of type D50 (CIE D50, ANSI PH 2.30, ISO 3664) and D65 (CIE D65).

* basic attributes concerning health, safety and energy saving acc. to EN14041

Our technical data sheets are constantly updated and adapted to the state of the art.

CLASSEN Holz Kontor GmbH, Werner-von-Siemens-Str. 18-20, DE-56759 Kaisersesch

This edition replaces all previous versions and is valid at the time of writing.

This document is valid without signature.